GIFU SHELLAC MANUFACTURING CO., LTD.

1-27, NISHIMARU-CHO, KANO, GIFU 500-8618 JAPAN

TEL:81-58-272-0831 FAX:81-58-272-0704, 81-58-272-2637

GIFU SHELLAC

POLYETHYLENE DISPERSION

HIGH FLAT Z.J-22

Featuring

: HIGH FLAT ZJ-22 is the dispersion of low molecular weight polyethylene in n-butyl acetate.

HIGH FLAT ZJ-22 is the best additives for paints and other coatings.

HIGH FLAT ZJ-22 give your finishes the properties of mar resistance and matting.

Appearance: Milky white dispersion

Typical properties: Wax content (%)

15

Particle size av. (μm)

 $5 \sim 6$

Maximum particle size(μ m)

 $20 \sim 25$

Remarks: 1.Store at $0 \, \text{°C} \sim 3 \, 5 \, \text{°C}$

Keep away from the place in sunshine and heat generator.

2. Use up quickly at opening.

The remnant is a factor of small numerous lumps with secondary cohesion from evaporation of solvent at product adhered inner surface.

3. Avoid heating and cooling.

If not so, it's dispersoid will be changing and it's viscosity will be rising.

Please avoid the generation of heat by high-speed mixing.

4. Shake the vessel at using.

Please confirm the fluidity. In cold storage (ex. winter), the product will be gelation temporarily.

5. Handle with care to ventilation and safeguard to avoid poisoning from inhalation of toluene and esters.

Packing : Net 15 kg in

18L steel JERRI CAN.

170 kg in 200L steel drum.

Dec. 2008